

Technical Data Sheet

UPS 210 CR Efficiency Fluid Ceramic



UPS 210 CR Super Low Friction Efficiency Ceramic is a high performance solvent free coating designed for use as a resurfacing and lining system to improve the efficiency in fluid flow environments.

UPS 210 CR is based on a specifically selected blend of epoxy resins and non toxic polyamino curing agents reinforced with carbide and inert flow enhancing pigments which produces a system with optimum physical and mechanical strengths and excellent resistance to erosion and corrosion.

UPS 210 CR is simple, safe and easy to use and its excellent low friction surface improves flow rates in pumps and pipelines which makes it an ideal choice for the protection of water boxes, tube sheets pumps, impeller, valves and heat exchangers.

Product Features

- Combines good application characteristics with good erosion and corrosion resistance.
- Designed for application by brush.
- Provides a low friction surface improving flow rates in pumps etc.,
- Designed for resurfacing and lining metal components.

Product Applications

Suitable for the coating of equipment such as pump cases and impellers, valves, pipes, propellers, rudders, jet tubes, kort nozzles etc.

Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.

Surface Preparation

All oil and grease must be removed from the surface of the repair using UPS CLEANER MEK.

For optimum performance, the surface should be abrasive blasted to ISO 8501/4 Standard Sa2.5 (SSPC SP10/NACE 2) and a minimum blast profile of 75 microns using angular abrasive. Once blast cleaned, the surface must be degreased and cleaned using UPS CLEANER MEK or similar type material. All surfaces must be repaired before gingering or oxidation occurs.

PLEASE NOTE For salt contaminated surfaces the area must be abrasive blast cleaned as mentioned above and left for 24 hours to allow any ingrained salts to come to the surface. After this 24 hour period the surface must be washed with UPS CLEANER MEK prior to brush blasting to remove the surface salts. This process must be repeated until all ingrained contaminants have been sweated out of the surface.

On surfaces already rebuilt with UPS 105 EG Metal Repair Paste or UPS 200 EG Ceramic Repair Paste no further surface preparation is required where over-coating times place within 3 hours. After this maximum over-coating time has elapsed roughen the surface by flash blasting or other means of abrasion.

Mixing & Application

Warm the Base component to 15 – 25°C (60 – 77°F) before mixing and do not apply when the ambient or substrate temperature is below 5°C (40°F) or less than 3°C (37°F) above the dew point.

Mixing of the product can be on full units or by part-mixing. If mixing the whole unit, pour the contents of the Activator unit into the Base container, ensuring that as much material is drained from the Activator container as possible. Mix the two components together until they are streak-free using a spatula and apply using a short bristled brush or applicator tool.

The product should be applied at a target wet film thickness of 250-350 microns (10-14 mil) per coat. The product must be applied to any metallic surface in two coats to give a minimum dry film thickness of 500 microns (20 mil). From commencement of mixing the material should be used within 30 – 40 minutes at 20°C (68°F).

As soon as possible after application of the first layer, and after no longer than 6 hours, apply a further coat as above. If the maximum over-coating time is exceeded, the first layer should be brush blasted or abraded before applying the second coat.

For part mixing use a mixing ratio of 5:1 by weight or 3:1 by volume.

Technical Data & Performance Characteristics

Coverage Rates

1KG (2.2LB) of fully mixed product will give the following coverage rates -	
2.716m ² at 250 microns	29ft ² at 10 mil
2.226m ² at 300 microns	24ft ² at 12 mil
1.935m ² at 350 microns	20.5ft ² at 14 mil
<i>Please note that the coverage rates quoted are theoretical and do not take into consideration the profile or condition of the surface being repaired.</i>	



Unique Polymer Systems LTD,
Unit 19, Link Business Centre,
Link Way, Malvern, Worcestershire,
WR14 1 UQ, United Kingdom,
+ 44 (0) 1531 63 63 00
sales@uniquepolymersystems.com



Technical Data Sheet

UPS 210 CR Efficiency Fluid Ceramic

Drying & Cure Times at 20°C (68°F)

Useable Life	30 – 40 minutes
Movement Without Load or Immersion	6 hours
Machining & Light Loading	10 hours
Full Loading & Cold Water Immersion	3 days
Hot Water & Chemical Immersion	6 days
<i>Once hardener, the material should be left for the following periods of time at 20°C (68°F) before being subjected to the conditions indicated. These times will be doubled at 10°C (50°F) and halved at 30°C (86°F)</i>	

For Optimum Performance

After an initial curing period of at least 4 hours at 20°C (68°F), raising the cure temperature progressively to 60 – 100°C (140 – 212°F) for up to 8 hours will result in improved mechanical, thermal and chemical resistance properties.

Appearance

Mixed Material Colour	Thixotropic Blue or Light Grey Liquid
Base Component Colour	Blue or Light Grey Paste
Activator Component	Amber Liquid

Over Coating Times

Minimum	The applied material can be over coated as soon as it is touch dry
Maximum	The over coating time should not exceed 6 hours
<i>Where the maximum over coating time is exceeded, the material should be allowed to harden before being abraded or flash blasted to remove surface contamination.</i>	

Shelf Life

5 years if unopened and store in normal dry conditions (15-30°C / 60-86°F)

Mixing Ratio

Component	Base	Activator
By Weight	5	1
By Volume	3	1

Density

Base	1.67
Activator	1.05
Mixed	1.52

Volume Capacity

657cc/Kg

Solids Content

100%

Slump Resistance

Nil at 400 microns

Pack Sizes

This product is available in the following pack sizes; 1KG (2.2LB), 3KG (6.6LB), 30KG (66LB)

Useable Life

10°C (50°F)	50 – 60 minutes
20°C (68°F)	30 – 40 minutes
30°C (86°F)	20 – 25 minutes

Mechanical Properties

Abrasion Resistance Taber CS17 Wheels / 1KG load	122mg loss / 1000 cycles 0.08cc loss / 1000 cycles
Tensile Shear Adhesion ASTM D1002 (Abrasive Blasted Mild Steel with 75 micron profile)	187kg/cm (2,650 psi)
Compressive Strength ASTM D695	735kg/cm (10,450 psi)
Corrosion Resistance ASTM B117	Minimum 5000 hours
Flexural Strength ASTM D790	570kg/cm (8,100 psi)
Hardness Rockwell R ASTM D785	85
Heat Distortion ASTM D648 At 264psi Fibre Stress	20°C (68°F) Cure – 46°C (115°F) 100°C (212°F) Cure – 82°C (180°F)

Heat Resistance

Suitable for long-term water immersion at temperatures up to 70°C (158°F).

Resistant to dry heat in excess of 200°C (392°F) dependent on load.

Chemical Resistance

The product resists attack by a wide variety of inorganic acids, alkalis, salts and organic media. Refer to the Unique Polymer Systems LTD Technical Centre for advice.

Quality: All Unique Polymer Systems LTD Products are supplied under the scopes of the company's fully documented quality system.

Warranty: Unique Polymer Systems LTD warrants that the performance of the product supplied will confirm to the typical descriptions quoted within this Technical Data Sheet provided the material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health & Safety: Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read the fully detailed Material Safety Data Sheet.

Legal Notice: The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Unique Polymer Systems LTD accepts no liability arising out of the use of this information or the product described herein.



Unique Polymer Systems LTD,
Unit 19, Link Business Centre,
Link Way, Malvern, Worcestershire,
WR14 1 UQ, United Kingdom,
+ 44 (0) 1531 63 63 00
sales@uniquepolymersystems.com

